

All New DTF PET Film

Suitable for a variety of textiles. This PET film for DTF printers is designed for quality, consistency, and ease of use.



APPLICATION INSTRUCTIONS

Step 1 – Print your pattern on PET film:

Select mirror printing, and print the pattern on the PET film.

Step 2 – Put hotmelt powder on:

Sprinkle the hotmelt powder evenly on the printed film, shake off the excess powder.

Step 3 – Drying printed PET film and melting powder process:

Dry & melt hotmelt powder through conveyor belt or heat press. Via conveyor belt: set the temperature at 248 °F. Via heat press: 293°F, 20s.

Step 4 – Transfer the pattern:

Transfer onto garment with a heat press at 266°F - 10s or 284 °F - 8s.

Step 5 – Peel:

Peel while cold or warm.

SPECIFICATIONS

| | |
|-------------------------------|---|
| STORAGE LIGHTING | Keep away from sunlight. |
| COMPOSITION | PET FILM |
| THICKNESS | 75 micron |
| Storage Life and Temp. | Up to 1 year. Store in a dry room at 59°F - 86°F. |
| INK COMPATIBILITY | Pigment Inks |
| APPLICATIONS | Cotton, Polyester, Acrylic, and similar fibers (except sublimation fabrics) |
| TEMPERATURE | 266°F - 284°F 8s-10s |
| PRESSURE | Medium |
| PEEL | Warm or Cold |

PRODUCT HIGHLIGHTS

- Superb matte designs.
- Quick pressing time, only requires 8-10 seconds.
- Low pressing temperature at only 266°F - 285°F.
- Consistent high quality film for complete print uniformity.
- Can be pressed onto most textiles.
- Peel warm or cold.
- Works with any DTF Printer.

CARE & MAINTENANCE

- Respect the garment instructions.
- Follow the instructions provided by the printer manufacturer. Printing at 113° F and drying temperature 149° F.
- Always use pigment inks.
- Wait 24 hours before the first wash.
- Avoid the use of aggressive products.
- Preferably wash inside out to extend design life.
- Do not bleach.

NOTE: We highly recommend that you perform tests before production.