



FIRSTMARK



VINYL



120°C
*134 = 150°C



PEEL : COLD



Flex Blade 45°
Medium Pressure



110µm
(132-111-131-126) : 215µm



20 Sec
*134 = 15 Sec

SPECIFICATIONS

THICKNESS:  **110 microns**
(132-111-131-126) : 215µm

CARRIER: Adhesive & Transparent polyester

CERTIFICATES:  **Oeko-Tex Label Standard 100 Class 1**
 **Oeko-Tex Label Standard 100 Class 2: ref 113 ref 129**

APPLICATION

1. Cut the material in reverse with a Flex regular blade
2. Weed the excess material
3. Heat press on a SEFA machine on the garment at 120°C & Protect the polyester carrier with silicone paper 20 sec - medium pressure
4. Peel the carrier off when cold



APPLIES ON

Cotton • Polyester • Acrylic & Similar Fibres

CARE & MAINTENANCE

- Always respect the garment's instructions
- Allow 24 hours after application before washing
- Iron the backside only

WASH

- Max 60° C
- Preferably inside out
- Do not bleach
- Tumble-dry approved
- Dry-cleaning unapproved

STORE

- Up to 1 year
- In a dry room (15-30° C)
- Away from sunlight
- In vertical position

Chemica
Heat transfers for textiles