



GALAXY



PU



160° C
*1107 : 180°C



PEEL : COLD



Flock Blade 60°
Medium Pressure



140 - 200 µm



20 Sec.

SPECIFICATIONS

APPLICATION

1. Cut the material in reverse with a Flock blade
2. Weed the excess material
3. Heat press on a SEFA machine on the garment at 160° C (1107:180°C) & Protect the polyester carrier with silicone paper 20 sec - medium pressure
4. Peel the carrier off when cold

THICKNESS:  Polyurethane 140 - 200 microns

CARRIER: Adhesive & Transparent polyester



APPLIES ON

Cotton • Polyester • Acrylic & Similar Fibres

CARE & MAINTENANCE

- Always respect the garment's instructions
- Allow 24 hours after application before washing
- Iron the backside only

WASH

- Max 60° C
- Preferably inside out
- Do not bleach
- Tumble-dry approved
- Dry-cleaning approved

STORE

- Up to 1 year
- In a dry room (15-30° C)
- Away from sunlight
- In vertical position

**Chemica**
Heat transfers for textiles

NOTE: For best results, it is recommended to TEST prior to starting standard production