



COTTON AND POLYESTER



POLYURETHANE



75 µm



Flex blade
45°



Medium to high
Pressure



Low
Temperature

120°C

20s

Quick
application

140°C

5s



HOT
or COLD
Peel

NYLON



POLYURETHANE



75 µm



Flex blade
45°



Medium to high
Pressure



Standard

140°C

20s



HOT
Peel

SPECIFICATIONS

APPLICATION

1. Cut the material in reverse with a Flex regular blade.
2. Weed the excess material.
3. Heat press using a SEFA machine on the garment following instructions (time and temperature) & Protect the polyester carrier with silicone paper.
4. Peel the carrier off when cold or hot.



THICKNESS: 75 microns

CARRIER: Adhesive & Transparent polyester

CERTIFICATES:



Oeko-Tex Label Standard 100 Class 1



Oeko-Tex Label Standard 100 Class 2



APPLIES ON

Cotton • Polyester • Acrylic • Similar Fibres • Nylon

CARE & MAINTENANCE

- Always respect the garment's instructions
- Allow 24 hours after application before washing
- Iron the backside only

WASH

- Max 60°C : Cotton & Polyester
Max 40°C : Nylon
- Preferably inside out
- Do not bleach
- Tumble-dry approved
- Dry-cleaning approved

STORE

- Up to 1 year
- In a dry room (15-30° C)
- Away from sunlight
- In vertical position