



SUNMARK



VINYL
POLYURETHANE*
*(4114 / 4107)



100°C



PEEL : COLD



Flex Blade 45°




135 µm
PU : 80µm



15 Sec

SPECIFICATIONS

THICKNESS:  Vinyl 135 microns/ Polyurethane 80 microns

CARRIER: Adhesive & Transparent polyester

APPLICATION

1. Cut the material in reverse with a Flex regular blade
2. Weed the excess material
3. Heat press on a SEFA machine on the garment at 100° C & Protect the polyester carrier with silicone paper
15 sec - medium pressure
4. Peel the carrier off when cold



APPLIES ON

Awnings and heat sensitive fabrics

CARE & MAINTENANCE

- Always respect the garment's instructions
- Allow 24 hours after application before washing
- Iron the backside only
- There is no warranty against U.V. rays.

WASH

- Do not wash

STORE

- Up to 1 year
- In a dry room (15-30° C)
- Away from sunlight
- In vertical position

Chemica
Heat transfers for textiles

NOTE: For best results, it is recommended to TEST prior to starting standard production