



REFLEX

497 - 498 - 493 - 491 - 494 - 492 - 495



POLYURETHANE



160°C - 3s
160°C - 15s



PEEL : HOT



Flex Blade 45°
Medium Pressure



200 µm

SPECIFICATIONS

APPLICATION

1. Cut the material in reverse with a Flex blade
2. Weed the excess material
3. Heat pressing on a SEFA machine in two steps:
1st : position and heat press the heat transfer on the garment protected by a silicon paper at 160°C - 3 sec. Remove the application tape immediately after heat pressing.
2nd : heat pressing without application tape at 160°C - 15sec.

THICKNESS:  Reflective polyurethane material
200 microns

CARRIER: Self-adhesive and clear polyester.



APPLIES ON

Cotton ● Polyester ● Acrylic & Similar Fibres

CARE & MAINTENANCE

- Always respect the garment's instructions
- Allow 24 hours after application before washing
- Iron the backside only

WASH

- Max 40° C
- Preferably inside out
- Do not bleach
- Tumble-dry approved
- Dry-cleaning approved

STORE

- Up to 1 year
- In a dry room (15-30° C)
- Away from sunlight
- In vertical position

Chemica
Heat transfers for textiles